

## Evaluation Guideline

For the KOMO® (technical approval-with) product certificate of

Plastics piping systems of PP intended for floor heating



Set up by CvD LSK d.d. 11 July 2016

Accepted by the KOMO Quality- and Certification  
commission d.d. 25 October 2016

# Preface Kiwa

This Evaluation Guideline has been prepared by the Kiwa Board of Experts LSK, in which the parties interested in the field of plastics piping systems of PP intended for floor heating systems, are represented. This Board of Experts also guides the performance of certification and adjusts this Evaluation Guideline where necessary. Wherever the term 'Board of Experts' is used in this Evaluation Guideline, the above-mentioned Board of Experts is meant.

Kiwa will use this Evaluation Guideline in conjunction with the Kiwa Regulations for Product Certification. These regulations detail the methods employed by Kiwa for conducting the necessary investigations prior to issuing the (technical approval-with-)product certificate and the method of the external control.

## **Binding declaration**

This Evaluation Guideline is declared binding by Kiwa per 25 October 2016.

### **Kiwa Nederland B.V.**

Sir W. Churchill-laan 273  
P.O. Box 70  
2280 AB RIJSWIJK ZH  
The Netherlands

Tel +31 (0)88 998 44 00  
Fax +31 (0)88 998 44 20  
info@kiwa.nl  
www.kiwa.nl

© 2016 Kiwa N.V.

All rights reserved. No part of this publication may be reproduced and/or published by means of printing, photocopying, microfilm or in any other manner whatsoever without the publisher's prior permission in writing. Without prejudice of the approval by the "KOMO Kwaliteits- en Toetsingscommissie" all rights rests with Kiwa. The use of this evaluation guideline for any purpose whatsoever shall only be allowed after the conclusion of a written agreement with Kiwa in which the right of use is arranged



## Preface

This amendment sheet belongs to the evaluation guideline BRL 5612 “Plastics piping systems of PP intended for floor heating” dated 25 October 2016 and shall be used by the certification institutes which are accredited by the Dutch Accreditation Council (RvA), or have submitted an application for this, and which have a license agreement with Stichting KOMO, as a supplement for the handling when dealing in addition to the evaluation guideline with applications for the issue or maintenance of a (technical approval-with-)product certificate for plastics piping systems of PP intended for floor heating.

This amendment sheet is:

- Validated by the Board of Experts LSK d.d. 09-12-2022
- Accepted by KOMO Kwaliteits- en Toetsingscommissie d.d. 21-02-2023

## Description of the change

Adding of the material PP-RCT, adaption of text in some paragraphs to the new format and updating standards.

In the evaluation guideline the following parts will be changed:

- Replace current §1.3 (→1.4) by §1.4 in this amendment sheet
- Replace current §1.4 (→1.5) door §1.5 in this amendment sheet
- Renumber paragraph 1.3, 1.4 and 1.5 to paragraph 1.4, 1.5 and 1.6
- Add paragraph 1.3 and 9.1 as stated in this amendment sheet
- Replace paragraph 1.1, 1.2, 4.3 Table 2, 5.1.1 Table 3, 5.2.2. Table 5, 5.2.5.1 Table 6, 5.2.5.2 Table 7/8/9/10/11 and 5.2.6 by the paragraphs and tables in this amendment sheet
- Change paragraph 2.5 and 9.2 as stated in this amendment sheet

### 1.1 General

The requirements embodied in this evaluation guideline (BRL) shall be employed by certification institutes, that are accredited by the Dutch Accreditation Council (RvA) and which have a license agreement with Stichting KOMO, when dealing with applications for the issue or maintenance of a (technical approval-with-)product certificate for plastics piping systems of PP intended for floor heating.

Besides the requirements embodied in this evaluation guideline, certification institutes impose additional requirements in the sense of requirements with regard to general procedures for certification as laid down in the general certification regulations of the respective certification body.

During the execution of certification activities, the certification bodies have to fulfil the requirements as laid down in the chapter ‘Requirements imposed on the certification body’.



### 1.3 Validity

This amendment sheet is an addition to the associated evaluation guideline BRL 5612 dated 25-10-2016. The technical approval-with-)product certificates issued on the basis of that evaluation guideline retain their validity.

New (technical approval-with-)product certificates may be issued on the basis of the above mentioned version of the evaluation guideline for a period of maximal 3 months after publication of this amendment sheet.

The validity period of the (technical approval-with-)product certificates is indefinite. The validity period can be restricted (ended) by:

- A change of this evaluation guideline,
- Failure of the certificate holder to meet his obligations.

### 1.4 Relation to European Regulation construction products (CPR, EU 305/2011)

On the products belonging to the range of this evaluation guideline, no harmonized European standard is applicable..

### 1.5 Acceptance of test reports delivered by the supplier

If the supplier submits reports from research bodies or laboratories to show that the requirements of the evaluation guideline are met, then these reports have to be prepared by a body meeting the prevailing accreditation standard, i.e.:

NEN-EN-ISO/IEC 17020 for inspection bodies;

NEN-EN ISO/IEC 17021-1 for certification bodies certifying systems;

NEN-EN-ISO/IEC 17025 for laboratories;

NEN-EN-ISO/IEC 17065 for certification bodies certifying products, processes and services

An body is deemed to meet these criteria if it can submit an accreditation certificate for the subject in question, issued by the Dutch Accreditation Council (RvA) or another accreditation institution that has been accepted as a member of a multilateral agreement on mutual recognition and acceptance of accreditation, which have been drawn up within EA, IAF and ILAC. If no accreditation certificate can be submitted, the certification body will assess whether the accreditation criteria have been met

### 2.5 Abbreviations

Add:

PP-RCT polypropylene random polymer with modified crystallinity



**Par 4.3 Table 2**

Table 2 - Tightness and strength of the pipe joints

| Aspect  | Requirements  | Test parameters  | Test method       |                         |                         |                         |                         |                         |  |
|---|---|--|-------------------|-------------------------|-------------------------|-------------------------|-------------------------|-------------------------|--|
| Resistance of mounted assemblies to temperature cycling   | no leakage  | 5000 cycles<br>T <sub>max</sub> = (80 ± 2) °C<br>T <sub>min</sub> = (20 ± 2) °C<br>t <sub>cyclus</sub> = 30 min <sup>1)</sup><br>p <sub>D</sub> (bar)<br>Pre-stress PP-B = 3,0 MPa<br>Pre-stress PP-R = 2,4 Mpa<br>Pre-stress PP-RCT = 2,7 MPa<br>One test piece | NEN-EN-ISO 19893  |                         |                         |                         |                         |                         |  |
| Resistance to pull-out under constant longitudinal force <sup>3)</sup>  | no separation of pipe and fitting<br>no scratches or breakage within the distance d (= diameter of the pie) on the pipe and fitting | t = (60 ± 1) min.<br>3 test pieces<br>F = 1,5 x π/4 x D <sub>n</sub> <sup>2</sup> x 1 (N)<br>D <sub>n</sub> in mm  | NEN-EN-ISO 3501   |                         |                         |                         |                         |                         |  |
| Leaktightness under vacuum <sup>3)</sup>  | Δp ≤ 0,05 bar   | t = (60 ± 1) min.<br>3 test pieces<br>p = -0,8 bar   | NEN-EN-ISO 13056  |                         |                         |                         |                         |                         |  |
| Leaktightness under internal pressure of assemblies subjected to bending (D <sub>n</sub> > 32 mm) <sup>3)</sup> | no leakage  | t = (60 ± 1) min.<br>3 test pieces   | NEN-EN-ISO 3503   |                         |                         |                         |                         |                         |  |
|   |   | Test pressure <sup>2)</sup> (bar)  |                   |                         |                         |                         |                         |                         |  |
|   |   | PP-B   |                   | PP-R                    | PP-RCT                  |                         |                         |                         |  |
|   |   | p <sub>D</sub><br>4 bar  |                   | p <sub>D</sub><br>6 bar | p <sub>D</sub><br>4 bar | p <sub>D</sub><br>6 bar | p <sub>D</sub><br>4 bar | p <sub>D</sub><br>6 bar |  |
|   |   |  |                   |                         |                         |                         |                         |                         |  |
|   |   | 32.9   | 49.4              | 23.1                    | 29.2                    | 18,2                    | 24,5                    |                         |  |
| Resistance to inner water pressure (strength joints)  | no leakage  | t = 1000 h.<br>T = 80°C<br>Minimum of 3 test pieces  | NEN-EN-ISO 1167-1 |                         |                         |                         |                         |                         |  |
|   |   | Test pressure <sup>2)</sup> (bar)  |                   |                         |                         |                         |                         |                         |  |
|   |   | PP-B   |                   | PP-R                    | PP-RCT                  |                         |                         |                         |  |
|   |   | p <sub>D</sub><br>4 bar  |                   | p <sub>D</sub><br>6 bar | p <sub>D</sub><br>4 bar | p <sub>D</sub><br>6 bar | p <sub>D</sub><br>4 bar | p <sub>D</sub><br>6 bar |  |
|   |   | 7,6  | 11,5              | 6,6                     | 8,3                     | 6,1                     | 8,2                     |                         |  |

<sup>1)</sup> t<sub>cyclus</sub> = t<sub>Tmax</sub> + t<sub>Tmin</sub> (= 15<sub>0</sub><sup>+1</sup> + 15<sub>0</sub><sup>+1</sup> = 30<sub>0</sub><sup>+2</sup>) minutes. Total time = 2500 hours)

<sup>2)</sup> For design stress see 5.2.2.

<sup>3)</sup> Not for weld fittings.



**Par. 5.1.1 Table 3**

Table 3 – Requirements for plastics fittings

| Aspect  | Requirement   | Test parameters  | Test method                                       |
|---|---|--|---|
| Material fitting body   | relevant product standard for the plastic used  | IQC <sup>1)</sup>  | Information producer                              |
| Long-term strength material fitting body  | ≥ design stress ( $\sigma_D$ ) according to the relevant product standard of the plastic at class 5 | Resistance to internal Hydrostatic pressure <sup>2)</sup><br>- at 20 °C<br>- between 60 °C and 80 °C<br>- at 95 °C<br>- at 110 °C                      | NEN-EN-ISO 1167-1 with the aid of NEN-EN-ISO 9080 |
| Appearance  | Smooth, without any irregularities  | Flawlessness   | Visual assessment                                 |
| Dimensions  | Specification producer  | Construction drawings  | NEN-EN-ISO 3126                                   |
| Rubber  | BRL 2013  | BRL 2013   | BRL 2013  |
| MFR (for PP fittings)   | ≤ 30% difference with respect to granulated material  | Mass 2,16 kg<br>Temperature 230 °C<br>Test period 10 min   | NEN-EN-ISO 1133-1                                 |
| Weerstand tegen impact (PP fittingen)   | < 10% breuk   | Test temperatuur 0°C<br>10 proefstukken  | ISO 9854-1  |
| Resistance to internal pressure : Thermal stability material fitting body   | Test time > 8760 h  | Resistance to internal hydrostatic pressure <sup>2)</sup> at 110 °C<br>Stress is accordance with the long term strength data                           | NEN-EN-ISO 1167-1                                 |
| Influence of heating fitting body   | Damage around point of connection ≤ 30 % of wall thickness<br>No holes, bubbles or cracks           | In consultation with manufacturer  | NEN-EN-ISO 580                                    |
| Resistance to inner water pressure (strength joints)  | no leakage  | t = 1000 h.<br>T = 80°C<br>Minimum of 3 test pieces  | NEN-EN-ISO 1167-1                                 |
|   |   | Test pressure <sup>2)</sup> (bar)  |   |
|   |   | PP-B                      PP-R                      PP-RCT   |   |
|   |   | p <sub>D</sub> 4 bar      p <sub>D</sub> 6 bar      p <sub>D</sub> 4 bar      p <sub>D</sub> 6 bar      p <sub>D</sub> 4 bar      p <sub>D</sub> 6 bar |   |
|   |   | 7,6      11,5      6,6      8,3      6,1      8,2  |   |
| <sup>1)</sup> Choice of material is free. The chosen material is listed in the IQC.<br><sup>2)</sup> Test pieces can be extruded or injection molded tubular test pieces<br><sup>3)</sup> For design stress see sub-paragraph 5.2.2 |   |  |   |

**Par. 5.2.2 Tabel 5**

Table 5 – minimum design stress for class 4

| Type PP | Design stress $\sigma_D$ ( N/mm <sup>2</sup> ) |
|---------|--|
| PP-B    | 1,94   |
| PP-R    | 3,29   |
| PP-RCT  | 3,67   |



**Par. 5.2.5.1 Tabel 6**

Table 6 – requirements and test methods for PP pipes

| Aspect   | Eis  | Test parameter   |         | Test methode        |
|--|--|--|---------|---------------------|
| Appearance   | Smooth without any flaws                                   | Flawlessness   |         | Visuele beoordeling |
| Dimensions of different layers   | Information manufacturer                                   | Construction drawings  |         | NEN-EN-ISO 3126     |
| MFR<br>PP material   | ≤ 0,5 g/10 min   | Massa 2,16 kg<br>Temperature 230 °C<br>Test period 10 min  |         | NEN-EN-ISO 1133-1   |
| MFR<br>PP-pipe   | ≤ 30%<br>difference with respect to<br>granulated material | Mass 2,16 kg<br>Temperature 230 °C<br>Test period 10 min   |         | NEN-EN-ISO 1133-1   |
| Resistance to internal<br>pressure <sup>1)</sup><br>PP-B   | Test time (uur)  | T (°C)   | σ (MPa) | NEN-EN-ISO 1167-1   |
|  | ≥ 1  | 20   | 16,0    |                     |
|  | ≥ 22   | 95   | 3,5     |                     |
|  | ≥ 165  | 95   | 3,0     |                     |
|  | ≥ 1000   | 95   | 2,6     |                     |
| Thermal stability PP-B   | ≥ 8760   | 110  | 1,4     |                     |
| Resistance to internal<br>pressure <sup>1)</sup><br>PP-R   | ≥ 1  | 20   | 16,0    |                     |
|  | ≥ 22   | 95   | 4,3     |                     |
|  | ≥ 165  | 95   | 3,8     |                     |
|  | ≥ 1000   | 95   | 3,5     |                     |
| Thermal stability PP-R   | ≥ 8760   | 110  | 1,9     |                     |
| Resistance to internal<br>pressure <sup>1)</sup><br>PP-RCT   | ≥ 1  | 20   | 15,0    |                     |
|  | ≥ 22   | 95   | 4,2     |                     |
|  | ≥ 165  | 95   | 4,0     |                     |
|  | ≥ 1000   | 95   | 3,8     |                     |
| Thermal stability PP-RCT   | ≥ 8760   | 110  | 2,6     |                     |
| Melting temperature<br>adhesive  | ≥ 120 °C   | DSC method   |         | NEN-EN-ISO 11357-3  |
| Resistance to impact   | < 10% defects  | Test temperature 0°C<br>10 test pieces   |         | ISO 9854-1          |
| Longitudinal reversion of<br>complete pipe   | ≤ 2%   | Change in length<br>150°C for PP-B<br>135°C for PP-R<br>135°C for PP-RCT<br>1 h e <sub>n</sub> ≤ 8 mm<br>2 h 8 mm < e <sub>n</sub> ≤ 16 mm<br>4 h e <sub>n</sub> > 16 mm |         | NEN-EN-ISO 2505     |
| Oxygen permeability <sup>2)</sup>  | ≤ 0,13 mg O <sub>2</sub> /m <sup>2</sup> .dag              | 40 °C  |         | NEN-ISO 17455       |
| <sup>1)</sup> For initial evaluation and yearly inspection the 1000 hours test at 95 °C is carried out. The other testing times can be applied during production control.<br><sup>2)</sup> Because the required value is expressed in a surface area unit, it is sufficient to measure the smallest diameter of the diameter series of the manufacturer (as long as the same wall thickness of the barrier layer applies to all diameters). For the purpose of inspection also larger diameters can be tested. |  |  |         |                     |



**Par.5.2.5.2 Table 7, 8, 9,10 en 11**

Table 7 - Calculated maximum value of S (Scalc, max )

| design pressure<br>(p <sub>D</sub> ) | Application class 4 |      |        |
|--------------------------------------|---------------------|------|--------|
|                                      | Scalc max. a)       |      |        |
|                                      | PP-B                | PP-R | PP-RCT |
| 4 bar b)                             | 4,9                 | 6,9  | 8,2    |
| 6 bar                                | 3,2                 | 5,5  | 6,1    |

1) The values are rounded to the nearest decimal.  
2) The maximum allowed Scalc,max = 6,3

Table 8 – Dimensions of the pipes for dimension group A (dimensions according to ISO 4065 and applicable for all classes within the application conditions)

Dimensions in millimeters

| Nominal size<br>DN/OD | Nominal outside diameter<br><br>d <sub>n</sub> | Mean outside diameter<br><br>d <sub>em,min</sub>   d <sub>em,max</sub> |      | Pipe series                                    |     |     |       | Absolute e <sub>min</sub> PP <sup>1)</sup> |                         |                         |                         |                         |                         |
|-----------------------|--|--|------|--|-----|-----|-------|--|-------------------------|-------------------------|-------------------------|-------------------------|-------------------------|
|                       |  |  |      | S 6,3  | S 5 | S 4 | S 3,2 | PP-B                                       |                         | PP-R                    |                         | PP-RCT                  |                         |
|                       |  |  |      | Wall thickness<br>(incl. barrier layer)        |     |     |       | p <sub>D</sub><br>4 bar                    | p <sub>D</sub><br>6 bar | p <sub>D</sub><br>4 bar | p <sub>D</sub><br>6 bar | p <sub>D</sub><br>4 bar | p <sub>D</sub><br>6 bar |
|                       |  |  |      | e <sub>min</sub> e <sub>n</sub> e <sub>n</sub> |     |     |       |  |                         |                         |                         |                         |                         |
| 12                    | 12   | 12   | 12,3 | 1,0  | 1,1 | 1,4 | 1,7   | 1,2  | 1,6                     | 1,0                     | 1,0                     | 1,0                     | 1,0                     |
| 14                    | 14   | 14   | 14,3 | 1,1  | 1,3 | 1,6 | 1,9   | 1,3  | 1,9                     | 1,0                     | 1,2                     | 1,0                     | 1,1                     |
| 16                    | 16   | 16   | 16,3 | 1,3  | 1,5 | 1,8 | 2,2   | 1,5  | 2,2                     | 1,1                     | 1,4                     | 1,0                     | 1,3                     |
| 20                    | 20   | 20   | 20,3 | 1,4  | 1,9 | 2,3 | 2,8   | 1,9  | 2,7                     | 1,4                     | 1,7                     | 1,2                     | 1,6                     |
| 25                    | 25   | 25   | 25,3 | 1,8  | 2,3 | 2,8 | 3,5   | 2,4  | 3,3                     | 1,7                     | 2,1                     | 1,5                     | 1,9                     |
| 32                    | 32   | 32   | 32,3 | 2,3  | 2,9 | 3,6 | 4,4   | 3,0  | 4,3                     | 2,2                     | 2,7                     | 1,9                     | 2,5                     |

1) Absolute calculated minimum wall thickness of the PP material with a minimum of 1.0 mm

Table 9 – Dimensions of the pipes for dimension group B1 (dimensions based on copper sizes and applicable for all classes within the application conditions)

Dimensions in millimeters

| Nominal size<br>DN/OD | Nominal outside diameter<br><br>d <sub>n</sub> | Mean outside diameter<br><br>d <sub>em,min</sub>   d <sub>em,max</sub> |      | Wall thickness<br>(incl. barrier layer) |     | Scalc | Absolute e <sub>min</sub> PP <sup>1)</sup> |                         |                         |                         |                         |                         |
|-----------------------|--|--|------|---|-----|-------|--|-------------------------|-------------------------|-------------------------|-------------------------|-------------------------|
|                       |  |  |      |   |     |       | PP-B                                       |                         | PP-R                    |                         | PP-RCT                  |                         |
|                       |  |  |      |   |     |       | p <sub>D</sub><br>4 bar                    | p <sub>D</sub><br>6 bar | p <sub>D</sub><br>4 bar | p <sub>D</sub><br>6 bar | p <sub>D</sub><br>4 bar | p <sub>D</sub><br>6 bar |
| 10                    | 10   | 9,9  | 10,2 | 1,5                                     | 1,5 | 2,8   | 1,0  | 1,4                     | 1,0                     | 1,0                     | 1,0                     | 1,0                     |
|                       |  |  |      | 1,8                                     | 1,7 |       |  |                         |                         |                         |                         |                         |
| 12                    | 12   | 11,9   | 12,2 | 1,5                                     | 1,5 | 3,4   | 1,2  | 1,6                     | 1,0                     | 1,0                     | 1,0                     | 1,0                     |
|                       |  |  |      | 2,0                                     | 1,9 |       |  |                         |                         |                         |                         |                         |
| 15                    | 15   | 14,9   | 15,2 | 1,5                                     | 1,5 | 4,4   | 1,4  | 2,0                     | 1,1                     | 1,3                     | 1,0                     | 1,2                     |
|                       |  |  |      | 2,5                                     | 2,4 |       |  |                         |                         |                         |                         |                         |
| 18                    | 18   | 17,9   | 18,2 | 1,7                                     | 1,7 | 4,8   | 1,7  | 2,4                     | 1,3                     | 1,5                     | 1,1                     | 1,4                     |
|                       |  |  |      | 2,5                                     | 2,4 |       |  |                         |                         |                         |                         |                         |
| 22                    | 22   | 21,9   | 22,2 | 2,0                                     | 2,0 | 5     | 2,1  | 2,9                     | 1,5                     | 1,9                     | 1,3                     | 1,7                     |
|                       |  |  |      | 3,0                                     | 2,9 |       |  |                         |                         |                         |                         |                         |
| 28                    | 28   | 27,9   | 28,2 | 2,6                                     | 2,6 | 4,9   | 2,6  | 3,7                     | 1,9                     | 2,4                     | 1,7                     | 2,2                     |
|                       |  |  |      | 4,0                                     | 3,9 |       |  |                         |                         |                         |                         |                         |

1) Absolute minimale wanddikte van het PP materiaal met een minimum van 1.0 mm





Table 10 – Dimensions of the pipes for dimension group B2 (dimensions based on Irish copper sizes ISO4065 and applicable for all classes within the application conditions)

Dimensions in millimeters

| Nominal size DN/OD | Nominal outside diameter<br>$d_n$ | Mean outside diameter<br>$d_{em,min}$   $d_{em,max}$ |       | Wall thickness (incl. barrier layer)<br>$e_{min}$ | $S_{calc}$ | Absolute $e_{min}$ PP <sup>1)</sup> |                   |                |                |                |                |
|--------------------|-----------------------------------|--|-------|---|------------|-------------------------------------|-------------------|----------------|----------------|----------------|----------------|
|                    |                                   |  |       |   |            | PP-B                                |                   | PP-R           |                | PP-RCT         |                |
|                    |                                   |  |       |   |            | $p_D$<br>4 bar                      | $p_D$<br>6 bar    | $p_D$<br>4 bar | $p_D$<br>6 bar | $p_D$<br>4 bar | $p_D$<br>6 bar |
| 14,7               | 14,7                              | 14,63  | 14,74 | 1,6   | 4,1        | 1,4                                 | 2,0 <sup>2)</sup> | 1,0            | 1,3            | 1,0            | 1,2            |
| 21                 | 21                                | 20,98  | 21,09 | 2,05  | 4,6        | 2,0 <sup>2)</sup>                   | 2,8 <sup>2)</sup> | 1,5            | 1,8            | 1,3            | 1,6            |
| 27,4               | 27,4                              | 27,33  | 27,44 | 2,6   | 4,8        | 2,6 <sup>2)</sup>                   | 3,7 <sup>2)</sup> | 1,9            | 2,3            | 1,6            | 2,1            |
| 34                 | 34                                | 34,08  | 34,19 | 3,15  | 4,9        | 3,2 <sup>2)</sup>                   | 4,5 <sup>2)</sup> | 2,3            | 2,9            | 2,0            | 2,6            |

<sup>1)</sup> Absolute calculated minimum wall thickness of PE-X material with a minimum of 1.0 mm  
<sup>2)</sup> For a 6 and/or 10 bar system this wall thickness is not permitted due to the fact that the required wall thickness is larger than the nominal wall thickness.

Table 11 – Dimensions of the pipes for dimension group C – heating systems

Dimensions in millimeters

| Nominal size DN/OD | Nominal outside diameter<br>$d_n$ | Mean outside diameter<br>$d_{em,min}$   $d_{em,max}$ |      | Wall thickness (incl. barrier layer)<br>$e_{min}$ | $S_{calc}$ | Absolute $e_{min}$ PP <sup>1)</sup> |                   |                |                |                |                |
|--------------------|-----------------------------------|--|------|---|------------|-------------------------------------|-------------------|----------------|----------------|----------------|----------------|
|                    |                                   |  |      |   |            | PP-B                                |                   | PP-R           |                | PP-RCT         |                |
|                    |                                   |  |      |   |            | $p_D$<br>4 bar                      | $p_D$<br>6 bar    | $p_D$<br>4 bar | $p_D$<br>6 bar | $p_D$<br>4 bar | $p_D$<br>6 bar |
| 12                 | 12                                | 12   | 12,3 | 2,0   | 2,5        | 1,2                                 | 1,6               | 1,0            | 1,0            | 1,0            | 1,0            |
| 14                 | 14                                | 14   | 14,3 | 2,0   | 3,0        | 1,3                                 | 1,9               | 1,0            | 1,2            | 1,0            | 1,1            |
| 15                 | 15                                | 15   | 15,3 | 2,0   | 3,2        | 1,4                                 | 2,0 <sup>2)</sup> | 1,1            | 1,3            | 1,0            | 1,2            |
| 16                 | 16                                | 16   | 16,3 | 2,0   | 3,5        | 1,5                                 | 2,2 <sup>2)</sup> | 1,1            | 1,4            | 1,0            | 1,3            |
| 17                 | 17                                | 17   | 17,3 | 2,0   | 3,8        | 1,6                                 | 2,3 <sup>2)</sup> | 1,2            | 1,5            | 1,0            | 1,3            |
| 18                 | 18                                | 18   | 18,3 | 2,0   | 4,0        | 1,7                                 | 2,4 <sup>2)</sup> | 1,3            | 1,5            | 1,1            | 1,4            |
| 20                 | 20                                | 20   | 20,3 | 2,0   | 4,5        | 1,9                                 | 2,7 <sup>2)</sup> | 1,4            | 1,7            | 1,2            | 1,6            |

<sup>1)</sup> Absolute calculated minimum wall thickness of PE-X material with a minimum of 1.0 mm  
<sup>2)</sup> For a 6 and/or 10 bar system this wall thickness is not permitted due to the fact that the required wall thickness is larger than the nominal wall thickness.

### 5.2.6 Certification mark

The following marks and indications must be provided on each product and product packaging in a clear, legible and indelible way:

- KOMO (or KOMO® word mark) + class 4 / design pressure;
- certificate number of the accompanying technical approval(system)certificate;
- manufacturer's name, trade name, system name or logo;
- material identification : PP-B, PP-R or PP-RCT;
- construction pipe: PP-B(R(CT))/EVOH, PP-B(R(CT))/EVOH/PP-B(R(CT)) or PP-B(R(CT))/Al/PP-B(R(CT));
- nominal outside diameter and nominal wall thickness in mm.
- production code.



## 9. List of documents

### 9.1 Requirements under public law

There are no requirements under public law applicable.

### 9.2 Normative documents

The following documents are changed in relation to the date of issue:

|  |  |
|--|--|
| ISO 4065:2018 en                                 | Thermoplastic pipes - Universal wall thickness table   |
| NEN-EN-ISO 1133-1: 2022                          | Plastics - Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics - Part 1: Standard method                      |
| NEN-EN 1254-3: 2021                              | Copper and copper alloys - Plumbing fittings - Part 3: Fittings with compression ends for use with plastics pipes  |
| NEN-EN 1254-6:2021                               | Copper and copper alloys - Plumbing fittings - Part 6: Fittings with push-fit ends   |
| NEN-EN 1254-8:2021                               | Copper and copper alloys - Plumbing fittings - Part 8: Fittings with press ends for use with plastics and multilayer pipes                                 |
| BRL 2013:2016+WB:2018                            | Vulcanized rubber products for hot and cold non-drinking water applications  |
| NEN-EN-ISO 3501:2022                             | Plastics piping systems - Mechanical joints between fittings and pressure pipes - Test method for resistance to pull-out under constant longitudinal force |
| NEN-EN 10283:2019 en                             | Corrosion resistant steel castings   |
| NEN-EN-ISO 11357-3: 2018 en                      | Plastics - Differential scanning calorimetry (DSC) - Part 3: Determination of temperature and enthalpy of melting and crystallization                      |
| ISO 11922-1: 2018 en                             | Thermoplastics pipes for the conveyance of fluids - Dimensions and tolerances - Part1: Metric series   |
| NEN-EN-ISO 15874-2: 2013/<br>Amd1:2018/Amd2:2022 | Plastic piping systems for hot and cold water installations – Polypropylene (PP) –Part 2   |

The following documents are added:

|                           |  |
|---------------------------|--|
| NEN-EN-ISO 13056: 2018 en | Plastics piping systems - Systems for hot and cold water - Test method for leaktightness under vacuum  |
| NEN-EN-ISO 19893: 2018 en | Plastics piping systems - Thermoplastics pipes and fittings for hot and cold water - Test method for the resistance of mounted assemblies to temperature cycling |

The following documents are removed:

|                    |  |
|--------------------|--|
| NEN-EN 12293: 2000 | Plastics piping systems - Thermoplastics pipes and fittings for hot and cold water - Test method for the resistance of mounted assemblies to temperature cycling |
| NEN-EN 12294: 2000 | Plastics piping systems - Systems for hot and cold water - Test method for leaktightness under vacuum  |

#### Remark:

Every year it is checked whether the normative documents are still up-to-date. Changes to the applicable normative documents are published on the services page on the website of the certification institute that has drawn up this assessment guideline.

# Table of contents

|          |  |           |
|----------|--|-----------|
| <b>1</b> | <b>Introduction</b>  | <b>3</b>  |
| 1.1      | General  | 3         |
| 1.2      | Field of application   | 3         |
| 1.3      | Relation to European Regulation constructionproducts (CPR, EU 305/2011)        | 3         |
| 1.4      | Acceptance of test reports delivered by the supplier                           | 4         |
| 1.5      | (Technical approval-with-)product certificate                                  | 4         |
| <b>2</b> | <b>Terminology</b>   | <b>5</b>  |
| 2.1      | General definitions  | 5         |
| 2.2      | Geometrical terminology and definitions  | 5         |
| 2.3      | Terms and definitions related to service conditions                            | 7         |
| 2.4      | Symbols  | 9         |
| 2.5      | Abbreviations  | 9         |
| <b>3</b> | <b>Procedure for obtaining a (technical approval-with-)product certificate</b> | <b>10</b> |
| 3.1      | Initial investigation  | 10        |
| 3.2      | Issue of the (technical approval-with-)product certificate                     | 10        |
| <b>4</b> | <b>Performances in the application</b>   | <b>11</b> |
| 4.1      | General  | 11        |
| 4.2      | Performance requirements   | 11        |
| 4.3      | Determination methods piping system  | 11        |
| <b>5</b> | <b>Product requirements and determination methods</b>                          | <b>13</b> |
| 5.1      | Fittings   | 13        |
| 5.2      | Pipes  | 15        |
| <b>6</b> | <b>Quality system requirements</b>   | <b>20</b> |
| 6.1      | General  | 20        |
| 6.2      | Manager of the quality system  | 20        |
| 6.3      | Internal quality control/quality plan  | 20        |
| 6.4      | Management of laboratory- and measure apparatus                                | 20        |
| 6.5      | Procedures and work instructions   | 20        |
| 6.6      | Other requirements imposed on the quality system                               | 20        |
| <b>7</b> | <b>Summary of tests and inspections</b>  | <b>21</b> |
| 7.1      | Testmatrix   | 21        |
| 7.2      | Evaluation of the quality system   | 22        |
| <b>8</b> | <b>Requirements imposed on the certification body</b>                          | <b>23</b> |

|           |  |           |
|-----------|--|-----------|
| 8.1       | General  | 23        |
| 8.2       | Certification staff                                  | 23        |
| 8.3       | Report initial tests                                 | 24        |
| 8.4       | Decision with regard to the issue of the certificate | 24        |
| 8.5       | Nature and frequency of external inspections         | 25        |
| 8.6       | Report to the Board of Experts                       | 25        |
| 8.7       | Interpretation of requirements                       | 25        |
| 8.8       | Sanction policy                                      | 25        |
| <b>9</b>  | <b>List of mentioned documents</b>                   | <b>26</b> |
| 9.1       | Norms/ normative documents:                          | 26        |
| <b>I</b>  | <b>example IQC-scheme for product manufacturer</b>   | <b>28</b> |
| <b>II</b> | <b>example IQC-scheme for system holders</b>         | <b>33</b> |

# 1 Introduction

## 1.1 General

The requirements embodied in this evaluation guideline (BRL) shall be employed by certification institutes, that are accredited by the Dutch Accreditation Council (RvA) and which have a license agreement with Stichting KOMO, when dealing with applications for the issue or maintenance of a (technical approval-with-)product certificate for plastics piping systems of PP intended for floor heating.

The technical field of this evaluation guideline is: F2 piping systems.

Besides the requirements embodied in this evaluation guideline, certification institutes impose additional requirements in the sense of requirements with regard to general procedures for certification as laid down in the general certification regulations of the respective certification body.

This evaluation guideline replaces BRL 5612 dated 05 February 2014. (Technical approval-with-)product certificates issued on the basis of that evaluation guideline and the alteration sheet lose their validity at most after one year after binding declaration.

During the execution of certification activities, the certification bodies have to fulfil the requirements as laid down in the chapter 'Requirements imposed on the certification body'.

## 1.2 Field of application

The products are intended to be applied in piping systems for hot water distribution for floor heating systems at a design pressure (= maximum operating pressure) of 6 bar (7 bar absolute or 6 bar overpressure), or 4 bar (5 bar absolute or 4 bar overpressure) under the conditions mentioned in table 1.

Remark:

Each pressure mentioned in this evaluation guideline is defined as overpressure. (So, with "6 bar" a "6 bar overpressure" is meant).

Table 1 – Temperature profile during 50 years

|                          | Temperature [ °C] | Lifetime                  | Overall service coefficient |
|--------------------------|-------------------|---------------------------|-----------------------------|
| T <sub>cold</sub>        | 20                | 2,5 years                 | 1,4                         |
| T <sub>design</sub>      | 40<br>+<br>60     | 20 years<br>+<br>25 years | 1,5                         |
| T <sub>max</sub>         | 70                | 2,5 years                 | 1,3                         |
| T <sub>malfunction</sub> | 100               | 100 hours                 | 1,0                         |

Remark: the mentioned temperature profile is in accordance with class 4 of NEN- ISO 10508.

## 1.3 Relation to European Regulation constructionproducts (CPR, EU 305/2011)

On the products belonging to the range of this evaluation guideline, no harmonized European standard is applicable.

#### 1.4 Acceptance of test reports delivered by the supplier

If the supplier submits reports from research bodies or laboratories to show that the requirements of the evaluation guideline are met, then these reports have to be prepared by a body meeting the prevailing accreditation standard, i.e.:

- NEN-EN-ISO/IEC 17020 for inspection bodies;
- NEN-EN ISO/IEC 17021-1 for certification bodies certifying systems;
- NEN-EN-ISO/IEC 17024 for certification bodies certifying persons;
- NEN-EN-ISO/IEC 17025 for laboratories;
- NEN-EN-ISO/IEC 17065 for certification bodies certifying products.

Explanation

NEN-EN-ISO/IEC 17021-1 is published on 1 juli 2015 and will replace NEN-EN-ISO/IEC 17021. A transition period of 2 years is in place.

The body is deemed to meet these criteria if an accreditation certificate can be submitted which has been issued by the Dutch Accreditation Council (RvA) or an accreditation body with which the Dutch Accreditation Council has concluded a mutual acceptance agreement. This accreditation should relate to the tests required for this evaluation guideline.

If no accreditation certificate can be submitted, the certification body shall verify whether the accreditation standard has been met or repeat the tests concerned either self or by a third party.

#### 1.5 (Technical approval-with-)product certificate

Based on the KOMO-systematic in appliance to this (technical approval-with-)product certificate, a KOMO®:

- Technical approval-with-product certificate for the piping system is issued. In the technical approval-with-product certificate products with their dimensions, material type and color, which are a part of the system, are listed, which comply to the requirements as stated in chapter 4, 5 en 6 of this evaluation guideline.
- Product certificate for the fittings and/ or pipes for the technical approval-with-product certificate in question. In the product certificate products with their dimensions, material type and color, are listed which comply to the requirements as listed in chapter 5 and 6 of this evaluation guideline.

On the website of the KOMO foundation ([www.komo.nl](http://www.komo.nl)) the models (technical approval-with-)product certificates are listed, which are applicable for this evaluation guideline. The (technical approval-with-)product certificate which will be issued is to be in accordance to this.

## 2 Terminology

For definitions in coherence to certification, one is referred to the website of the KOMO foundation ([www.komo.nl](http://www.komo.nl)) and the regulations of the certifying body.

### 2.1 General definitions

#### 2.1.1 IQC-scheme

A description of the quality inspections carried out by the manufacturer as part of this quality system.

#### 2.1.2 Flexible piping system

A piping system in which possible bends in the pipe can be made without any mechanical means and in which the pipe is not deformed due to the possible bends.

#### 2.1.3 Manifolds

An apparatus by which an incoming water flow is divided (adjustable) over several outlets.

#### 2.1.4 Mechanical joints

A connection between a pipe and a fitting, made by means of pressing a ring or case over the outside diameter of the pipe, with or without extra sealing elements and possibly making use of a supporting ring in the pipe, according to NEN-EN ISO 6708.

#### 2.1.5 Piping system

The total of pipes, protection pipes, fittings, bends, expansion pieces, valves and other piping components.

#### 2.1.6 Rigid piping system

A piping system in which possible bends in the pipe has to be made by mechanical means.

#### 2.1.7 Supplier

The party responsible for ensuring that the design of products continuously fulfils the requirements of this evaluation guideline.

### 2.2 Geometrical terminology and definitions

#### 2.2.1 Calculated pipe value ( $S_{calc}$ )

Value for a specific pipe calculated according to the following equation, rounded up to the nearest 0,1 mm.

$$S_{calc} = \frac{d_n - e_n}{2 \times e_n}$$

In which:

$d_n$  = the nominal outside diameter in millimeters;

$e_n$  = the nominal wall thickness expressed in millimeters.

#### 2.2.2 Inside diameter (at any point) ( $d_i$ )

Measured inside diameter at any point, rounded up to the nearest 0,1 mm.

### 2.2.3 **Maximum calculated pipe value ( $S_{calc,max}$ )**

The maximum value of the calculated S value for a specific application class.  
The lowest value of:

$$\frac{\sigma_D}{p_D} \quad \text{or} \quad \frac{\sigma_{20}}{p_D} \quad (p_D = 1 \text{ MPa})$$

In which:

$\sigma_D$  = the design pressure after 50 years in MP applicable for a class 5 material.

$\sigma_{20}$  = the design pressure at 20 °C after 50 years in MPa

$p_D$  = the design pressure in MPa

### 2.2.4 **Maximum mean outside diameter ( $d_{em, max}$ )**

Maximum value for the mean outside diameter as specified for a given nominal size.

### 2.2.5 **Maximum wall thickness ( $e_{max}$ )**

Maximum wall thickness around the circumference of a component, as specified.

### 2.2.6 **Mean outside diameter ( $d_{em}$ )**

Measured outside diameter through its cross section at any point of a pipe or spigot end of a fitting in any cross section divided by  $\pi$  (=3,142), rounded up to the nearest 0,1 mm.

### 2.2.7 **Minimum mean outside diameter ( $d_{em, min}$ )**

Minimum value for the mean outside diameter as specified for a given nominal size.

### 2.2.8 **Minimum wall thickness ( $e_{min}$ )**

Minimum wall thickness around the circumference of a component, as specified.

### 2.2.9 **Nominal outside diameter ( $d_n$ )**

Specified outside diameter, in millimeters, assigned to a nominal size DN/OD.

### 2.2.10 **Nominal size (DN)**

Numerical designation of the size of a component, which is a convenient round number, approximately equal to the manufacturing dimensions in millimeters (mm).

### 2.2.11 **Nominal wall thickness ( $e_n$ )**

Numerical designation of the wall thickness of a component, approximately equal to the manufacturing dimension in millimeters (mm).

### 2.2.12 **Outside diameter (at any point) ( $d_e$ )**

Measured outside diameter through its cross section at any point of a pipe or spigot end of a fitting, rounded up to the nearest 0,1 mm.

### 2.2.13 **Out-of-roundness (ovality)**

Difference between the measured maximum outside diameter and the measured minimum outside diameter in the same cross-sectional plane of a pipe or spigot end of a fitting, or the difference between the measured maximum inside diameter and the measured minimum inside diameter in the same cross-sectional plane of a socket.

### 2.2.14 **Pipe series (S)**

Dimensionless number for pipe designation conforming to ISO 4065.

### 2.2.15 **Tolerance**

Permitted variation of the specified value of a parameter, expressed as the difference between the permitted maximum and the permitted minimum value.



### **2.2.16 Wall thickness (at any point) (e)**

Measured wall thickness at any point around the circumference of a component, rounded up to the nearest 0,1 mm.

## **2.3 Terms and definitions related to service conditions**

### **2.3.1 Cold-water temperature ( $T_{cold}$ )**

The temperature of the cold water with a maximum of 25 °C. For the calculation of the design pressure applications a water temperature of 20 °C is issued.

### **2.3.2 Design pressure( $p_D$ ).**

The allowable pressure in the piping system that, during continuous use, during 50 years may occur.

### **2.3.3 Hydrostatic tension $\sigma$**

Stress in the circumferences direction of the pipe wall caused by internal water pressure. This stress is deduced from the internal pressure according to the following formula:

$$\sigma = p \times \frac{(d_{em} - e_{min})}{20 \times e_{min}}$$

In which:

$\sigma$  = the stress in the circumference direction of the pipe wall in MPa

$p$  = the internal pressure in bar;

$d_{em}$  = the mean outside diameter of the pipe in mm;

$e_{min}$  = de minimum wall thickness of the pipe in mm.

### **2.3.4 Lifetime**

The time during which the piping system has to function with a certain operating temperature.

### **2.3.5 LPL**

The lower confidence level. A statistical unit representing the point above which 97,5 % of all values are found.

### **2.3.6 Malfunction temperature ( $T_{mal}$ )**

Highest temperature of the water to be conveyed depending on unintended conditions (i.e. exceeding of control limits) for which the system has been designed for, occurring for short periods only (max. 100 hours in 50 years).

### **2.3.7 Maximum design temperature ( $T_{max}$ )**

Highest temperature of the water to be conveyed depending on the service conditions for which the system has been designed for, occurring for a short period only.

### **2.3.8 Reference line**

By a group of experts determined minimum long-term strength hoopstress for a specific material.

### **2.3.9 Temperature profile**

The most frequently appearing temperatures that during 50 years occur during a certain time.

### **2.3.10 Operating temperature ( $T_{operation}$ )**

The temperature of the water to be conveyed depending on the service conditions for which the system has been designed for.

**2.3.11 Overall service (design)coefficient (C)**

Overall coefficient with a value greater than or equal to 1, which takes into consideration service conditions as well as properties of the components of a piping system other than those represented in the lower confidence limit, LPL.

**2.3.12  $\sigma_D$**

The design stress in MPa, applicable for a class 3 material with a temperature profile according to table 1.

**2.3.13  $\sigma_{LPL}$**

An unit expressed in wall stress, that represents the value of the 97,5% lower confidence level of the predicted stress for a single value at a temperature T and a time t.

**2.3.14  $\sigma_{LTHS}$**

An unit expressed in wall stress, that represents the value of 50% lower confidence interval of the predicted stress for a single value at a temperature T and a time t.

**2.3.15  $\sigma_T$**

The stress in MPa, applied to a test piece for a certain temperature and time.

## 2.4 Symbols

|                 |   |
|-----------------|---|
| C               | service (design) coefficient                                    |
| $d_e$           | outside diameter (at any point)                                 |
| $d_{em}$        | mean outside diameter   |
| $d_{em,min}$    | minimum mean outside diameter                                   |
| $d_{em,max}$    | maximum mean outside diameter                                   |
| $d_n$           | nominal diameter  |
| e               | wall thickness at any point                                     |
| $e_{max}$       | maximum wall thickness at any point                             |
| $e_{min}$       | minimum wall thickness at any point                             |
| $e_n$           | nominal wall thickness  |
| F               | force   |
| p               | pressure  |
| $p_D$           | design pressure   |
| $S_{calc}$      | calculated S-value  |
| $S_{calc,max}$  | maximum calculated S-value                                      |
| T               | temperature   |
| $T_{cold}$      | cold-water temperature  |
| $T_{operation}$ | operating temperature   |
| $T_{mal}$       | malfunction temperature   |
| $T_{max}$       | maximum design temperature                                      |
| t               | time  |
| $\sigma$        | hydrostatic stress  |
| $\sigma_{cold}$ | design stress at 20 °C  |
| $\sigma_D$      | design stress   |
| $\sigma_{DF}$   | design stress of the plastics fitting material                  |
| $\sigma_{DP}$   | design stress of the plastics pipe material                     |
| $\sigma_F$      | hydrostatic stress value of the plastics fitting material       |
| $\sigma_P$      | hydrostatic stress value of the plastics pipe material          |
| $\sigma_{LPL}$  | lower confidence interval of the long-term strength             |
| $\sigma_{LTHS}$ | hydrostatische spanning bij de betrouwbaarheidsinterval van 50% |

## 2.5 Abbreviations

|       |  |
|-------|--|
| CI    | Certification Institute                  |
| CPR   | Construction Products Regulation         |
| DN    | nominal size                             |
| DN/OD | nominal size related to outside diameter |
| EVOH  | Ethyleen-vinylalcohol                    |
| LPL   | lower confidence interval                |
| PP-B  | polypropylene block polymer              |
| PP-R  | polypropylene random polymer             |
| S     | S-value                                  |
| MFR   | melt flow rate                           |

## 3 Procedure for obtaining a (technical approval-with-)product certificate

### 3.1 Initial investigation

#### 3.1.1 *Technical approval-with-product certificate*

For the purpose of obtaining the KOMO technical approval-with-product certificate the certification institute will perform an investigation. The certification institute shall determine that the applicant is able to continuously manufacture products which meet the requirements in this guideline. The initial investigations consist of:

- Assessment if the internal quality system of the applicant meets the requirements of chapter 6 of this guideline.
- Determination and assessment of the performance in the application of the specified piping system and ascertain if the requirements of chapter 4 of this guideline are met.
- Assessment of the by the applicant provided or to provide documents in relation to the internal quality assurance to check if the with the products assembled piping system meets the performance requirements as laid down in this guideline.
- Assessment of the processing instructions and the terms of the application.

#### 3.1.2 *Product certificate*

For the purpose of obtaining the KOMO product certificate the certification institute will perform an investigation. The certification institute shall determine that the applicant is able to continuously manufacture products which meet the requirements in this guideline. The initial investigations consist of:

- Assessment if the internal quality system of the applicant meets the requirements of chapter 6 of this guideline.
- Inspection of the production and the finished product to determine if the product meets the requirements in chapter 5 of this guideline.
- Determination of the product characteristics (of the constituent products) as laid down in the guideline.

### 3.2 Issue of the (technical approval-with-)product certificate

After completion of the initial investigation, the results are presented to the decision-maker. The decision-maker evaluates the results and determines whether the certificate can be issued or whether additional information and/or investigations are required in order to be able to issue the (technical approval-with-)product certificate.

## 4 Performances in the application

### 4.1 General

In this chapter the performance requirements imposed on the plastics piping systems of PP intended for floor heating in its application are included, as well as the determination methods in order to be able to determine whether the requirements of the application are fulfilled. At setting the requirements the uncertainties of the measurements are taken into account. This implies that drawing conclusions whether requirements are fulfilled these uncertainties do not need to be weighted anymore.

### 4.2 Performance requirements

- The system needs to be adequately resistant to oxygen permeability
- All joints need to be leak proof and sufficiently tight to endure external influences.
- All parts of the system are required to be designed to have a life expectancy of 50 years at a temperature profile in accordance to class 4 from NEN-ISO 10508, at an operating pressure of 4 bar or 6 bar absolute.

### 4.3 Determination methods piping system

#### 4.3.1 General

The joints in the piping system have to be tested with regard to their proper functioning in accordance to table 2. In this chapter all joint tests required for the joint system are included. The combination of a (possible) rubber seal, pipe, (possible) supporting insert and clamp construction in the fitting have to be tested with regard to the aspects as mentioned in table 2.

#### 4.3.2 Tightness and strength of the joints

After testing in accordance with table 2, the piping system is sufficiently watertight and the pipe ends shall show no damage.

If not otherwise stated, the testing temperature is  $(23 \pm 2)$  °C.

#### 4.3.3 Installation instructions

The supplier shall provide installation instructions. The instruction shall be in the Dutch language and must contain specific information for construction of the joints. Also instructions must be given with regard to storage, transport and processing temperature.

Table 2 - Tightness and strength of the pipe joints

| Aspect  | Requirements  | Test parameters   | Test method       |  |
|---|---|---|-------------------|--|
| Resistance of mounted assemblies to temperature cycling   | no leakage  | 5000 cycles<br>$T_{max} = (80 \pm 2) \text{ } ^\circ\text{C}$<br>$T_{min} = (20 \pm 2) \text{ } ^\circ\text{C}$<br>$t_{cyclus} = 30 \text{ min } ^1$ .<br>$P_{D \text{ esign}}(\text{bar})$<br>Pre-stress PP-B = 3,0 MPa<br>Pre-stress PP-R = 2,4 MPa<br>One test piece | NEN-EN 12293      |  |
| Resistance to pull-out under constant longitudinal force  | no separation of pipe and fitting<br>no scratches or breakage within the distance d (= diameter of the pie) on the pipe and fitting | $t = (60 \pm 1) \text{ min.}$<br>Three test pieces<br>$F = 1,5 \times \pi/4 \times D_n^2 \times 1 \text{ (N)}$<br>$D_n$ in mm   | NEN-EN-ISO 3501   |  |
| Leaktightness under vacuum  | $\Delta P \leq 0,05 \text{ bar}$  | $t = (60 \pm 1) \text{ min.}$<br>Three test pieces<br>$P = -0,8 \text{ bar}$  | NEN-EN 12294      |  |
| Leaktightness under internal pressure of assemblies subjected to bending ( $\varnothing > 32 \text{ mm}$ )              | no leakage  | $t = (60 \pm 1) \text{ min.}$<br>Three test pieces  | NEN-EN 3503       |  |
|   |   | Test pressure (bar)   |                   |  |
|   |   | PP-B <sup>2)</sup> PP-R <sup>2)</sup>   |                   |  |
|   |   | $p_D$ 4 bar $p_D$ 6 bar $p_D$ 4 bar $p_D$ 6 bar   |                   |  |
|   |   | 32.8      49.2      23.2      29.1  |                   |  |
| Resistance to inner water pressure (strength joints)  | no leakage  | $t = 1000 \text{ h.}$<br>$T = 80^\circ\text{C}$<br>Minimum of 3 connections   | NEN-EN-ISO 1167-1 |  |
|   |   | Test pressure (bar)   |                   |  |
|   |   | PP-B <sup>2)</sup> PP-R <sup>2)</sup>   |                   |  |
|   |   | $p_D$ 4 bar $p_D$ 6 bar $p_D$ 4 bar $p_D$ 6 bar   |                   |  |
|   |   | 7,6      11,4      6,7      8,4   |                   |  |
| <sup>1)</sup> $t_{cyclus} = t_{Tmax} + t_{Tmin} (= 15_0^{+1} + 15_0^{+1} = 30_0^{+2})$ minutes. Total time = 2500 hour) |   |   |                   |  |
| <sup>2)</sup> For design stress see parapgraph 5.2.2.   |   |   |                   |  |

## 5 Product requirements and determination methods

In this chapter the product requirements are listed which de compounded products needs to meet, as well as the testing methods to determine these are met. At setting the requirements the uncertainties of the measurements are taken into account. This implies that drawing conclusions whether requirements are fulfilled these uncertainties do not need to be weighted anymore.

### 5.1 Fittings

Distributers (fittings with more than 2 outlets) can be part of a piping system, in which case have to comply to the demands stated in this chapter.

#### 5.1.1 Plastics fittings

The plastics fittings have to fullfil the requirements as listed in table 3.

Table 3 – Requirements for plastics fittings

| Aspect  | Requirement  | Test parameter   | Test method  |
|---|--|--|--|
| Material fitting body   | relevant product standard for the plastics used  | IQC <sup>1)</sup>  | Information producer                                 |
| Long-term strength material fitting body                                  | $\geq$ design stress ( $\sigma_D$ ) according to the relevant product standard at class 4      | Resistance to internal hydraulic pressure <sup>2)</sup><br>- at 20 °C<br>- between 60 °C and 80 °C<br>- at 95 °C<br>- at 110 °C  | NEN-EN-ISO 1167-1<br>With the aid of NEN-EN-ISO 9080 |
| Appearance  | Smooth, without any irregularities   | Flawlessness   | Visual assement                                      |
| Dimensions  | Specification producer   | Construction drawings  | NEN-EN-ISO 3126                                      |
| Rubber  | BRL 2013   | BRL 2013   | BRL 2013   |
| MFR (PP fittings)   | $\leq$ 30% difference with respect to granulated material                                      | Temperature 230 °C<br>Mass 2,16 kg<br>Temperature 230 °C<br>Test period 10 min   | NEN-EN-ISO 1133-1                                    |
| Resistance to impact (PP fittings)  | < 10% defects  | Test temperature 0°C<br>10 test pieces   | ISO 9854-1   |
| Resistance to internal pressure : Thermal stability material fitting body | Test time > 8760 h   | Resistance to internal hydraulic pressure <sup>2)</sup> At 110 °C<br>Stress is accordance with the long term strength data   | NEN-EN-ISO 1167- 1                                   |
| Influence of heating fitting body   | Damage around point of connection $\leq$ 30 % of wall thickness<br>No holes, bubbles or cracks | In consultation with manufacturer  | NEN-EN-ISO 580                                       |
| Resistance to inner water pressure (strength joints)                      | no leakage   | t = 1000 h<br>T = 80°C<br>Minimum of 3 test pieces<br>Test pressure (bar)<br>PP-B <sup>3)</sup> PP-R <sup>3)</sup><br>p <sub>D</sub> 4 bar   p <sub>D</sub> 6 bar   p <sub>D</sub> 4 bar   p <sub>D</sub> 6 bar<br>7,6      11,4      6,7      8,4 | NEN-EN-ISO 1167-1                                    |

<sup>1)</sup> Choice of material is free. The chosen material is listed in the IQC.  
<sup>2)</sup> Test pieces are blow moulded and are cylindrical shaped  
<sup>3)</sup> For design stress see sub-paragraph 5.2.2

### 5.1.2 Metal fittings

The metal mechanical fittings must fulfil the requirements of table 4.

Table 4 – requirements for metal fittings

| Aspect  | Eis  | Test parameter  | Test methode                |
|---|--|---|-----------------------------|
| Material fitting body   | <b>Messing:</b><br>NEN-EN1254-3<br>NEN-EN 1254-6<br>NEN-EN 1254-8<br><b>RVS:</b><br>NEN-EN 10088<br>NEN-EN 10283 | IQC <sup>1)</sup>   | Information manufacturer    |
| Rubber  | BRL 2013   | BRL 2013  | BRL 2013                    |
| Dimensions  | NEN-EN1254-3<br>NEN-EN 1254-6<br>NEN-EN 1254-8   | Minimum thickness   | NEN-EN-ISO 228-1 of ISO 7-1 |
| Construction  | NEN-EN1254-3<br>NEN-EN 1254-6<br>NEN-EN 1254-8   | Construction drawings   | NEN-EN-ISO 3126             |
| Resistance to inner water pressure (strength fitting body)  | No cracks  | <b>Brass:</b><br>NEN-EN1254-3 par. 5.1<br>NEN-EN 1254-6 Par. 5.1.4<br>NEN-EN 1254-8 Par.5.1.1<br><b>Stainless steel:</b><br>25 bar at (23 + 2) °C during 48 hours <sup>2)</sup> | NEN-EN-ISO 1167-1           |
| <b>Brass</b><br>Resistance to stress corrosion  | No cracks  | PH 9,5  | NEN-ISO 6957                |
| <b>Stainless steel:</b><br>Resistance to intercrystalline degradation   | No cracks  | Method A  | NEN-EN-ISO 3651-2           |
| <sup>1)</sup> Choice of material is free. The chosen material is listed in the IQC.<br><sup>2)</sup> The most critical wallthickness/ DN ratio is tested. |  |   |                             |

### 5.1.3 Certification mark

The following marks and indications must be provided on each product and product packaging in a clear, legible and indelible way:

The fittings shall be provided with at least the following marks:

- KOMO or KOMO® word mark (if not possible KOMO on only the smallest packaging);
- manufacturer's name, trade name or logo;
- nominal outside diameter in mm of the connecting pipe;
- production code

The smallest packaging unit of the fittings must be provided with at least the following information:

- KOMO (or KOMO® word mark);
- certificate number of the accompanying technical approval(system)certificate, in accordance with the marking of the connecting pipe;
- manufacturer's name, trade name, system name or logo;
- nominal outside diameter and nominal wall thickness in mm of the connecting pipe;
- material identification in case the fitting body is made of plastics.



## 5.2 Pipes

### 5.2.1 Introduction

In this chapter the requirements which the pipes have to meet as well as the test methods to determine this, are listed.

### 5.2.2 Classification of the PP material

The PP material must fulfil the specifications listed in NEN-EN-ISO 15874-2.

The calculated values for  $\sigma_D$  must be higher than or equal to the values in table 5.

Tabel 5 – minimum required wall stress for class 4

| Type PP | Design stress $\sigma_D$<br>( N/mm <sup>2</sup> ) |
|---------|---|
| PP-B    | 1,95  |
| PP-R    | 3,30  |

### 5.2.3 Construction of the pipe

The pipe can be composed of 3 or 5 layers. From inside to outside the following applies:

#### 3-layer pipe:

A PP inner layer, an adhesive layer, an oxygen barrier layer (e.g. EVOH).

#### 4-layer pipe:

An extra outer layer of a non-load bearing material (for example PP/adhesive) on the 3-layer pipe is possible.

#### 5-layer pipe:

- A PP inner layer, an adhesive layer, a plastics or metal oxygen barrier layer( i.e. EVOH or aluminum) , an adhesive layer, a PP outer layer.  
The wall thickness of the inner layer shall be at least 0,4 mm.  
The total of the wall thickness of both PP layers must comply with the appropriate requirement according to table 6.
- A PP inner layer, an adhesive layer, a plastics or metal oxygen barrier layer( i.e. EVOH or aluminum), an adhesive layer an outer layer of a non-stress bearing material (i.e. PE).  
The total of the wall thickness of the PP inner layer must comply with the appropriate requirement according to table 6.

### 5.2.4 Plastics barrier layer

The plastics barrier layer shall fulfil the following preconditions:

- o The mechanical characteristics of the pipe may not be adversely affected by this layer.
- o Information concerning the thickness of the layer and its tolerances, as well as the type and the supplier of the plastics barrier layer, shall be a part of the certification agreement.

## 5.2.5 Requirements for the pipes

The chosen material for the pipe is listed in the IQC.

### 5.2.5.1 Mechanical requirements for the pipe

For the different layers and the complete pipe the requirements according to table 6 apply.

Table 6 – requirements and test methods for PP pipes

| Aspect  | Requirements   | Test parameter   |         | Test method                |
|---|--|--|---------|----------------------------|
| Appearance  | Smooth without any flaws                                   | Flawlessness   |         | Visual inspection          |
| Dimensions of different layers  | Information manufacturer                                   | Construction drawings  |         | NEN-EN-ISO 3126            |
| MFR<br>PP material  | ≤ 0,5 g/10 min   | Massa 2,16 kg<br>Temperature 230 °C<br>Test period 10 min  |         | NEN-EN-ISO 1133-1          |
| MFR<br>PP-pipe  | ≤ 30%<br>difference with respect to<br>granulated material | Mass 2,16 kg<br>Temperature 230 °C<br>Test period 10 min   |         | NEN-EN-ISO 1133-1          |
| Resistance to internal<br>pressure <sup>1)</sup><br>PP-B  | Test time (h)  | T (°C)   | σ (MPa) | NEN-EN-ISO 1167-<br>series |
|   | ≥ 1  | 20   | 16,0    |                            |
|   | ≥ 22   | 95   | 3,5     |                            |
|   | ≥ 165  | 95   | 3,0     |                            |
|   | ≥ 1000   | 95   | 2,6     |                            |
| Thermal stability PP-B  | ≥ 8760   | 110  | 1,4     |                            |
| Resistance to internal<br>pressure <sup>1)</sup><br>PP-R  | ≥ 1  | 20   | 16,0    |                            |
|   | ≥ 22   | 95   | 4,3     |                            |
|   | ≥ 165  | 95   | 3,8     |                            |
|   | ≥ 1000   | 95   | 3,5     |                            |
| Thermal stability PP-R  | ≥ 8760   | 110  | 1,9     |                            |
| Melting temperature adhesive  | ≥ 120 °C   | DSC method   |         | NEN-EN-ISO 11357-3         |
| Resistance to impact  | < 10% defects  | Test temperature 0°C<br>10 test pieces   |         | ISO 9854-1                 |
| Longitudinal reversion of<br>complete pipe  | ≤ 2 %  | Change in length<br>150°C for PP-B<br>135°C for PP-R<br>1 h e <sub>n</sub> ≤ 8 mm<br>2 h 8 mm < e <sub>n</sub> ≤ 16 mm<br>4 h e <sub>n</sub> > 16 mm |         | NEN-EN-ISO 2505            |
| Oxygen permeability <sup>2)</sup>   | ≤ 0,13 mg O <sub>2</sub> /m <sup>2</sup> .day              | 40°C   |         | NEN-ISO 17455              |
| <sup>1)</sup> For initial evaluation and yearly inspection the 1000 hours test at 95 °C is carried out. The other testing times can be applied during production control.   |  |  |         |                            |
| <sup>2)</sup> Because the required value is expressed in a surface area unit, it is sufficient to measure the smallest diameter of the diameter series of the manufacturer (as long as the same wall thickness of the barrier layer applies to all diameters). For the purpose of inspection also larger diameters can be tested. |  |  |         |                            |

### 5.2.5.2 Dimensions

Each class, nominal size and minimum wall thickness must be chosen in such a way according table 8, 9, 10, 11 and 12 that the corresponding S-series or the  $S_{calc}$  is equal or smaller than the  $S_{calc, max}$  as indicated in table 7.

Table 7 – Calculated maximum value of S ( $S_{calc, max}$ )

| design pressure<br>( $p_D$ )                                  | Application class 4 |      |
|---|---------------------|------|
|   | $S_{calc, max.}^1)$ |      |
|   | PP-B                | PP-R |
| 4 bar <sup>2)</sup>   | 4,9                 | 6,9  |
| 6 bar   | 3,3                 | 5,5  |
| <sup>3)</sup> The values are rounded to the nearest decimals. |                     |      |
| <sup>4)</sup> The maximum allowed $S_{calc, max} = 6,3$       |                     |      |

Table 8 – Dimensions of the pipes for dimension group A (dimensions according to ISO 4065 and corresponding for all classes within the application conditions)

| Nominal size<br>DN/OD | Nominal outside diameter | Mean outside diameter |      | Pipe series                             |     |     |       |       |       | Dimensions in millimetres<br>Absolute $e_{min}$ PP <sup>1)</sup> |                |                |                |
|-----------------------|--------------------------|-----------------------|------|---|-----|-----|-------|-------|-------|--|----------------|----------------|----------------|
|                       |                          |                       |      | S 6,3                                   | S 5 | S 4 | S 3,2 | S 2,5 | S 2,0 | PP-B   |                | PP-R           |                |
|                       |                          |                       |      | Wall thickness<br>(incl. barrier layer) |     |     |       |       |       | $p_D$<br>4 bar   | $p_D$<br>6 bar | $p_D$<br>4 bar | $p_D$<br>6 bar |
|                       |                          |                       |      | $e_{min}$ and $e_n$                     |     |     |       |       |       |  |                |                |                |
| 12                    | 12                       | 12                    | 12,3 | 1,0                                     | 1,1 | 1,4 | 1,7   | 2,0   | 2,4   | 1,2  | 1,6            | 1,0            | 1,0            |
| 14                    | 14                       | 14                    | 14,3 | 1,1                                     | 1,3 | 1,6 | 1,9   | 2,3   | 2,8   | 1,3  | 1,9            | 1,0            | 1,2            |
| 16                    | 16                       | 16                    | 16,3 | 1,3                                     | 1,5 | 1,8 | 2,2   | 2,7   | 3,3   | 1,5  | 2,2            | 1,1            | 1,4            |
| 20                    | 20                       | 20                    | 20,3 | 1,4                                     | 1,9 | 2,3 | 2,8   | 3,4   | 4,1   | 1,9  | 2,7            | 1,4            | 1,7            |
| 25                    | 25                       | 25                    | 25,3 | 1,8                                     | 2,3 | 2,8 | 3,5   | 4,2   | 5,1   | 2,4  | 3,3            | 1,7            | 2,1            |
| 32                    | 32                       | 32                    | 32,3 | 2,3                                     | 2,9 | 3,6 | 4,4   | 5,4   | 6,5   | 3,0  | 4,3            | 2,2            | 2,7            |

<sup>1)</sup> Absolute calculated minimum wall thickness of the PP material with a minimum of 1.0 mm

Table 9 – Dimensions of the pipes for dimension group B1 (dimensions based on copper sizes and applicable for all classes within the application conditions)

Dimensions in millimeters

| Nominal size DN/OD | Nominal outside diameter | Mean outside diameter |                     | Wall thickness (incl. barrier layer) |                  | S <sub>calc</sub> | Absolute e <sub>min</sub> PP <sup>1)</sup> |                      |                      |                      |
|--------------------|--------------------------|-----------------------|---------------------|--------------------------------------|------------------|-------------------|--|----------------------|----------------------|----------------------|
|                    |                          |                       |                     |                                      |                  |                   | PP-B                                       |                      | PP-R                 |                      |
|                    |                          |                       |                     |                                      |                  |                   | p <sub>D</sub> 4 bar                       | p <sub>D</sub> 6 bar | p <sub>D</sub> 4 bar | p <sub>D</sub> 6 bar |
|                    | d <sub>n</sub>           | d <sub>em,min</sub>   | d <sub>em,max</sub> | e <sub>n</sub>                       | e <sub>min</sub> |                   |  |                      |                      |                      |
| 10                 | 10                       | 9,9                   | 10,2                | 1,5<br>1,8                           | 1,5<br>1,7       | 2,8<br>2,4        | 1,0  | 1,4                  | 1,0                  | 1,0                  |
| 12                 | 12                       | 11,9                  | 12,2                | 1,5<br>2,0                           | 1,5<br>1,9       | 3,4<br>2,6        | 1,2  | 1,6                  | 1,0                  | 1,0                  |
| 15                 | 15                       | 14,9                  | 15,2                | 1,5<br>2,5                           | 1,5<br>2,4       | 4,4<br>2,6        | 1,4  | 2,0                  | 1,1                  | 1,3                  |
| 18                 | 18                       | 17,9                  | 18,2                | 1,7<br>2,5                           | 1,7<br>2,4       | 4,8<br>3,2        | 1,7  | 2,4                  | 1,3                  | 1,5                  |
| 22                 | 22                       | 21,9                  | 22,2                | 2,0<br>3,0                           | 2,0<br>2,9       | 5<br>3,3          | 2,1  | 2,9                  | 1,5                  | 1,9                  |
| 28                 | 28                       | 27,9                  | 28,2                | 2,6<br>4,0                           | 2,6<br>3,9       | 4,9<br>3,1        | 2,6  | 3,7                  | 1,9                  | 2,4                  |

<sup>1)</sup> Absolute calculated minimum wall thickness of PP material with a minimum of 1.0 mm

Table 10 – Dimensions of the pipes for dimension group A (dimensions based on Irish cn ISO 4065 and applicable for all classes within the application conditions)

Dimensions in millimeters

| Nominal esize DN/OD | Nominal outside diameter | Mean outside diameter |                     | Wall thickness (incl. barrier layer) | S <sub>calc</sub> | Absolute e <sub>min</sub> PP <sup>1)</sup> |                      |                      |                      |
|---------------------|--------------------------|-----------------------|---------------------|--------------------------------------|-------------------|--|----------------------|----------------------|----------------------|
|                     |                          |                       |                     |                                      |                   | PP-B                                       |                      | PP-R                 |                      |
|                     |                          |                       |                     |                                      |                   | p <sub>D</sub> 4 bar                       | p <sub>D</sub> 6 bar | p <sub>D</sub> 4 bar | p <sub>D</sub> 6 bar |
|                     | d <sub>n</sub>           | d <sub>em,min</sub>   | d <sub>em,max</sub> | e <sub>min</sub>                     |                   |  |                      |                      |                      |
| 14,7                | 14,7                     | 14,63                 | 14,74               | 1,6                                  | 4,1               | 1,4  | 2,0 <sup>2)</sup>    | 1,0                  | 1,3                  |
| 21                  | 21                       | 20,98                 | 21,09               | 2,05                                 | 4,6               | 2,0 <sup>2)</sup>                          | 2,8 <sup>2)</sup>    | 1,5                  | 1,8                  |
| 27,4                | 27,4                     | 27,33                 | 27,44               | 2,6                                  | 4,8               | 2,6 <sup>2)</sup>                          | 3,7 <sup>2)</sup>    | 1,9                  | 2,3                  |
| 34                  | 34                       | 34,08                 | 34,19               | 3,15                                 | 4,9               | 3,2 <sup>2)</sup>                          | 4,5 <sup>2)</sup>    | 2,3                  | 2,9                  |

<sup>1)</sup> Absolute calculated minimum wall thickness PP material with a minimum of 1.0 mm  
<sup>2)</sup> For this system this material is not allowed because the minimum required wall thickness is larger than the nominal wall thickness

Tablel 11 – Dimensions of the pipes for dimension group C – heating systems

Dimensions in millimeters

| Nominal size DN/OD | Nominal size diameter | Mean outside diameter |                     | Wall thickness (incl. barrier layer) | S <sub>calc</sub> | Absolute e <sub>min</sub> PP <sup>1)</sup> |                      |                      |                      |
|--------------------|-----------------------|-----------------------|---------------------|--------------------------------------|-------------------|--|----------------------|----------------------|----------------------|
|                    |                       |                       |                     |                                      |                   | PP-B                                       |                      | PP-R                 |                      |
|                    |                       |                       |                     |                                      |                   | p <sub>D</sub> 4 bar                       | p <sub>D</sub> 6 bar | p <sub>D</sub> 4 bar | p <sub>D</sub> 6 bar |
|                    | d <sub>n</sub>        | d <sub>em,min</sub>   | d <sub>em,max</sub> | e <sub>min</sub>                     |                   |  |                      |                      |                      |
| 12                 | 12                    | 12                    | 12,3                | 2,0                                  | 2,5               | 1,2  | 1,6                  | 1,0                  | 1,0                  |
| 14                 | 14                    | 14                    | 14,3                | 2,0                                  | 3,0               | 1,3  | 1,9                  | 1,0                  | 1,2                  |
| 15                 | 15                    | 15                    | 15,3                | 2,0                                  | 3,2               | 1,4  | 2,0 <sup>2)</sup>    | 1,1                  | 1,3                  |
| 16                 | 16                    | 16                    | 16,3                | 2,0                                  | 3,5               | 1,5  | 2,0 <sup>2)</sup>    | 1,1                  | 1,4                  |
| 17                 | 17                    | 17                    | 17,3                | 2,0                                  | 3,8               | 1,6  | 2,2 <sup>2)</sup>    | 1,2                  | 1,5                  |
| 18                 | 18                    | 18                    | 18,3                | 2,0                                  | 4,0               | 1,7  | 2,4 <sup>2)</sup>    | 1,3                  | 1,5                  |
| 20                 | 20                    | 20                    | 20,3                | 2,0                                  | 4,5               | 1,9  | 2,7 <sup>2)</sup>    | 1,4                  | 1,7                  |

<sup>1)</sup> Absolute calculated minimum wall thickness of the PP material with a minimum 1.0 mm  
<sup>2)</sup> For a 6 bar system this material is not allowed because the minimum required wall thickness is larger than the nominal wall thickness

Table 12 – Tolerances for the wall thickness

Dimensions in millimetres

| Minimum wall thickness |   | Tolerance <sup>1)</sup> | Minimum wall thickness |   | Tolerance <sup>1)</sup> |
|------------------------|---|-------------------------|------------------------|---|-------------------------|
| e <sub>min</sub>       |   |                         | e <sub>min</sub>       |   |                         |
| >                      | ≤ | X                       | >                      | ≤ | X                       |
| 1                      | 2 | 0,3                     | 4                      | 5 | 0,6                     |
| 2                      | 3 | 0,4                     | 5                      | 6 | 0,7                     |
| 3                      | 4 | 0,5                     | 6                      | 7 | 0,8                     |

<sup>1)</sup> The tolerance is defined as (+X/0 mm) in which X is the value of the tolerance as mentioned in this table. The permitted tolerance corresponds to level 5 of ISO 11922-1.

### 5.2.6 Certification mark

The following marks and indications must be provided on each product and product packaging in a clear, legible and indelible way:

- KOMO (or KOMO® word mark) + class 4 / design pressure;
- certificate number of the accompanying technical approval(system)certificate;
- manufacturer's name, trade name, system name or logo;
- material identification : PP-B or PP-R;
- construction pipe : PP-B(R)/EVOH, PP-B(R)/EVOH/PP-B(R) of PP-B(R)/Al/PP-B(R)
- nominal outside diameter and nominal wall thickness in mm.
- production code.

# 6 Quality system requirements

## 6.1 General

This chapter contains the requirements that have to be met by the supplier's quality management system.

## 6.2 Manager of the quality system

Within the organisational structure an employee must be appointed who is in charge of managing the quality system.

## 6.3 Internal quality control/quality plan

The supplier must have an implemented and operational internal quality control scheme in place (IQC-scheme).

In this IQC-scheme the following must be demonstrably recorded:

- materials used in the product
- which aspects are checked by the manufacturer;
- according to which methods these inspections are carried out;
- how often these inspections are carried out;
- how the inspection results are registered and stored.

This IQC-scheme shall be derived from the example format as shown in the annex. The scheme must be detailed in such a way that it provides CI sufficient confidence that the requirements of this evaluation guideline are continuously fulfilled.

## 6.4 Management of laboratory- and measure apparatus

The supplier must determine which laboratory- and measure apparatus are needed based on this BRL in order to demonstrate the product fulfils the requirements.

When applicable laboratory- and measure apparatus need to be calibrated at specified intervals.

The supplier needs to validate and register the previous measure results, when at the time of calibration is determined that the laboratory and measure devices are not operating correctly.

The apparatus in question need to be marked in such a way that can be determined what the calibration status is.

The supplier is required to register the calibration results.

## 6.5 Procedures and work instructions

The supplier must be able to submit procedures for:

- storage of used materials and readied product;
- the handling of non-conforming products;
- corrective actions in case non-conformities are found;
- the handling of complaints regarding the products and/or services supplied;
- managing work instructions and inspection sheets in use.

## 6.6 Other requirements imposed on the quality system

In case the quality system of the supplier is certified on the basis of ISO 9001, a combination can be made with the IQC-scheme.

# 7 Summary of tests and inspections

## 7.1 Testmatrix

The table below contains a summary of the tests and inspections to be carried out in the event of certification. The following definitions are used.

- **Initial tests:** The test to determine if all demands are met as stated in the BRL.
- **Inspection:** the evaluation tests which is held after issuing of the certificate in order to determine if the certified products are meeting the demands continuously; thereby is lo noted at what frequency inspections by the certifying institute (CI) are needed.
- **Evaluation of the quality system:** evaluation of the compliance to the IKB schedule and procedures.

| Description of requirement   | Par. BRL | Test within the scope of |   |           | Change of raw material |
|--|----------|--------------------------|---|-----------|------------------------|
|  |          | Initial tests            | Surveillance by CI after issue of the certificate <sup>1)</sup> |           |                        |
|  |          |                          | Inspection <sup>2)</sup>  | Frequency |                        |
| <b>System requirements</b>   |          |                          |   |           |                        |
| Resistance of mounted assemblies to temperature cycling                  | 4.2      | X                        |   |           | X                      |
| Resistance to pull-out under constant longitudinal force                 |          | X                        |   |           |                        |
| Leaktightness under vacuum   |          | X                        |   |           |                        |
| Leaktightness under internal pressure of assemblies subjected to bending |          | X                        |   |           |                        |
| Resistance to internal pressure (strength joints)                        |          | X                        | X   | 1x year   | X                      |
| Installation instructions  |          | X                        |   |           |                        |
| <b>Requirements for plastics fittings/ dividers</b>                      |          |                          |   |           |                        |
| Material   | 5.1.1    | X                        | X   | 1x year   | X                      |
| Long-term strength   |          | X                        | X <sup>3)</sup>   | 1x year   | X                      |
| Dimensions   |          | X                        | X   | 1x year   | X                      |
| Rubber   |          | X                        |   |           | X                      |
| Degree of cross linking / MFR  |          | X                        | X   | 1x year   | X                      |
| Resistance to impact (PP fittings)                                       |          | X                        | X   | 1x year   | X                      |
| Resistance to inner water pressure (strength fitting body) (see system)  |          | X                        | X   | 1x year   | X                      |
| Appearance   |          | X                        | X   | 1x year   | X                      |
| Resistance to internal pressure: Thermal stability material fitting body |          | X                        |   |           | X                      |
| Influence of heating   |          | X                        |   |           | X                      |
| <b>Requirements for metal fittings/ dividers</b>                         |          |                          |   |           |                        |
| Material composition   | 5.1.2    | X                        | X   | 1x year   | X                      |
| Rubber   |          | X                        |   |           | X                      |
| Dimensions   |          | X                        | X   | 1x year   | X                      |
| Construction   |          | X                        |   |           | X                      |
| Resistance to internal pressure (strength body) see system               |          | X                        |   |           | X                      |
| Resistance to stress corrosion   |          | X                        |   |           | X                      |
| Resistance to intergranular corrosion                                    |          | X                        |   |           | X                      |

| Description of requirement                | Par. BRL | Test within the scope of |   |           | Change of raw material |
|---|----------|--------------------------|---|-----------|------------------------|
|   |          | Initial tests            | Surveillance by CI after issue of the certificate <sup>1)</sup> |           |                        |
|   |          |                          | Inspection <sup>2)</sup>  | Frequency |                        |
| <b>Requirements for the pipe</b>          |          |                          |   |           |                        |
| Long-term strength                        | 5.2.2    | X                        | X <sup>3)</sup>   |           | X                      |
| Appearance                                | 5.2.5    | X                        | X   | 1x year   | X                      |
| Material                                  |          | X                        | X   | 1x year   | X                      |
| Dimensions                                |          | X                        | X   | 1x year   | X                      |
| MFR                                       |          | X                        | X   | 1x year   | X                      |
| Resistance to impact                      |          | X                        |   |           | X                      |
| Melting temperature adhesive              |          | X                        |   |           | X                      |
| Resistance to internal hydraulic pressure |          | X                        | X   | 1x year   | X                      |
| Thermal stability pipe                    |          | X                        |   |           | X                      |
| Oxygen permeability                       |          | X                        | X   | 1x year   | X                      |
| Longitudinal reversion                    |          | X                        | X   | 1x year   | X                      |

<sup>1)</sup> In case the product or production process changes significantly, the performance requirements must be determined again.

<sup>2)</sup> By the site assessor or by the supplier in the presence of the site assessor all product properties that can be evaluated within the visiting time (maximum 1 day) are determined. In case this is not possible, an agreement will be made between the certification body and the supplier about how the inspection will take place.

<sup>3)</sup> This aspect is compared with the for this aspect ascertained acceptance parameters on the basis of the IQC inspection (indirect by means of direct related parameters).

## 7.2 Evaluation of the quality system

During each inspection visit the quality system of the supplier shall be examined and evaluated.



# 8 Requirements imposed on the certification body

## 8.1 General

The certification body has to be accredited for the subject of this BRL on the basis of NEN-EN-ISO/IEC 17065 by the Dutch Accreditation Council (RvA).

The certification body must have the disposal of a regulation, or an equivalent document, in which the general rules for certification are laid down. In particular these are:

- The general rules for carrying out the initial tests, to be distinguished in:
  - The way suppliers are informed about the handling of the application;
  - Execution of the initial tests;
  - The decision with regard to the initial tests executed.
- The general rules with regard to the execution of inspections and the inspection aspects to be employed;
- The measures to be taken by the certification body in the event of non-conformities;
- The measures to be taken by the certification body in the event of illegitimate use of certificates, certification marks, icons and trademarks;
- The rules for termination of the certificate;
- The possibility of lodging appeal against decisions or measures made by the certification body.

## 8.2 Certification staff

The staff involved in the certification is to be sub-divided into:

- Certification assessor/ Reviewer: in charge of review of the by the supplier supplied or to be supplied construction drawings and documents, admissions, reviewing of applications and the review of conformity assessments;
- Site assessor: in charge of carrying out external inspections at the supplier's works;
- Decision-maker: in charge of taking decisions in connection with the initial tests performed, continuing the certification in connection with the inspections performed and making decisions on the need of corrective actions.

### 8.2.1 Competence requirements

Distinguished are:

- Competence requirements for executive certification staff of a CI that fulfil the requirements of NEN-EN-ISO/IEC 17065;
- Competence requirements for executive certification staff of a CI that are in addition set up by the Board of Experts for the subject of this evaluation guideline.

The competencies of the relevant certification personnel must be visibly documented.

|   | <b>Certification assessor/ Reviewer</b>  | <b>Site assessor</b>  | <b>Decision-maker</b>                                      |
|---|--|---|--|
| <b>General competence</b>   |  |   |  |
| General education   | • Higher vocational education  | • Intermediate technical vocational education   | • Higher vocational education                              |
| Knowledge of company processes<br>Competence for professional evaluation  | • 1 year work experience   | • 2 years work experience<br>• Audit training   | • 5 years work experience of which 1 year in certification |
| <b>Technical competence</b>   |  |   |  |
| Knowledge of the BRL  | • Detailed knowledge of the specified BRL in question or the BRL's related to each other.  | • Witness inspection<br>• Knowledge of the chapters of the BRL which relate to the quality system and the tests.  | • n/a  |
| Relevant knowledge of: <ul style="list-style-type: none"> <li>• The technology involved with producing the products to be inspected, the execution of processes and the provisioning of services.</li> <li>• The way products are used, processes are applied and services are rendered;</li> <li>• Any deficiency that can occur during use of the product, any mistake that can be made during the use of a product and any imperfection in the rendering of services.</li> </ul> | <ul style="list-style-type: none"> <li>• Relevant technical higher vocational education work and intellectual level.</li> <li>• At least 1 year of experience in production, testing, inspection and or in the installation trade, including: <ul style="list-style-type: none"> <li>- 2x inspections under supervision</li> </ul> </li> <li>• Or internal training course including: <ul style="list-style-type: none"> <li>- 2x inspections under supervision</li> </ul> </li> </ul> | <ul style="list-style-type: none"> <li>• Intermediate technical vocational education work and intellectual level.</li> <li>• At least 1 year of experience in production, testing, inspection and or in the installation trade, including: <ul style="list-style-type: none"> <li>- 3x inspections under supervision</li> <li>- 1x independent inspection</li> </ul> </li> <li>• Or internal training course including: <ul style="list-style-type: none"> <li>- 3x inspections under supervision</li> <li>- 1x independent inspection</li> </ul> </li> </ul> | • n/a  |

### 8.2.2 Qualification

Certification staff must be demonstrably qualified by evaluation of education and experience of the above-mentioned requirements.

The authority for qualification rests with the management of the certification body

### 8.3 Report initial tests

The certification body records the results of the initial tests in a report. The report must fulfil the following requirements:

- **Completeness:** the report judges about all requirements of the evaluation guideline;
- **Traceability:** the findings whereupon the judgements are based must be recorded in a traceable way.

With regard to granting the certificate, the decision-maker must be able to base his decision upon the findings recorded in the report.

### 8.4 Decision with regard to the issue of the certificate

The decision with regard to the issue of the certificate must be made by a qualified decision-maker, who was not involved at the initial tests. The decision must be traceable recorded.

## **8.5 Nature and frequency of external inspections**

The certification body must enforce inspections at the supplier's site to investigate whether the obligations are met. The Board of Experts advises about the number of inspection visits required. At the time of validation of this evaluation guideline this frequency has been fixed at four inspection visits per year.

In case the quality system of the supplier is certified on the basis of ISO 9001, the frequency is set at 2 inspection visits per year.

If the supplier is the holder of a system (not a manufacturer of a pipe or a fitting), the frequency is set to 1 inspection a year.

If the supplier is a private label owner (identical certificate derived from an existing technical-with-approval product certificate) then the frequency is set at 1 inspection per 2 year.

Inspections shall invariably include:

- The IQC-scheme of the supplier and the results of tests carried out by the supplier;
- The correct marking of the certified products;
- The compliance with the required procedures.

The findings of the inspection visits performed shall be traceably recorded, by the certification body, in a report.

## **8.6 Report to the Board of Experts**

The certification body reports at least once a year about the certification activities performed. In this reporting, the following subjects must be addressed:

- Mutations in number of certificates (new/cancelled);
- Number of inspections carried out in relation to the fixed frequency;
- Results of the inspections;
- Measures imposed in case of non-conformities;
- Complaints received from third parties concerning certified products.

## **8.7 Interpretation of requirements**

The Board of Experts may lay down the interpretation of this evaluation guideline in a separate interpretation document.

The certification body is obliged to inform whether an interpretation document is available. If this is the case, then the interpretations as laid down in the interpretation document must be employed.

## **8.8 Sanction policy**

The sanction policy and the weighing of the non-conformities is available through the service page on the web-site of the certification institute who drafted this guideline.

# 9 List of mentioned documents

## 9.1 Norms/ normative documents:

|                         |  |
|-------------------------|--|
| ISO 7-1:1994+C1:2007    | Pipe threads where pressure-tight joints are made on the threads – Part 1: Dimensions, tolerances and designation  |
| NEN-EN- ISO 228-1: 2003 | Pipe threads where pressure-tight joints are not made on the threads - Part 1: Dimensions, tolerances and designation  |
| NEN-EN-ISO 580: 2005    | Plastics piping and ducting systems - Injection-moulded thermoplastics fittings - Methods for visually assessing the effects of heating                                    |
| NEN-EN-ISO 1133-1: 2011 | Plastics - Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics - Part 1: Standard method                                      |
| NEN-EN-ISO 1167-1:2006  | Thermoplastics pipes, fittings and assemblies for the conveyance of fluids - Determination of the resistance to internal pressure  |
| NEN-EN 1254-3: 1998     | Copper and copper alloys - Plumbing fittings - Part 3: Fittings with compression ends for use with plastics pipes  |
| NEN-EN 1254-6:2012      | Copper and copper alloys - Plumbing fittings - Part 6: Fittings with push-fit ends   |
| NEN-EN 1254-8:2012      | Copper and copper alloys - Plumbing fittings - Part 8: Fittings with press ends for use with plastics and multilayer pipes   |
| BRL 2013:2012+WB:2014   | Vulcanized rubber products for hot and cold non-drinking water applications  |
| NEN-EN-ISO 2505: 2005   | Thermoplastics pipes - Longitudinal reversion - Test method and parameters   |
| NEN-EN-ISO 3126: 2005   | Plastics piping systems - Plastics components - Determination of dimensions  |
| NEN-EN-ISO 3501:2015    | Plastics piping systems - Mechanical joints between fittings and pressure pipes - Test method for resistance to pull-out under constant longitudinal force                 |
| NEN-EN-ISO 3503:2015    | Plastics piping systems - Mechanical joints between fittings and pressure pipes - Test method for leaktightness under internal pressure of assemblies subjected to bending |
| ISO 4065:1996           | Thermoplastics pipes - Universal wall thickness table  |
| NEN-EN-ISO 6708: 1995   | Pipe components - Definition and selection of DN (nominal size)  |
| NEN-ISO 6957:1988       | Copper alloys - Ammonia tests for stress corrosion resistance  |
| ISO 9001:2015           | Quality management systems – Requirements  |
| NEN-EN-ISO 9080: 2012   | Plastics piping and ducting systems - Determination of the long-term hydrostatic strength of thermoplastics materials in pipe form by extrapolation                        |

|                               |  |
|-------------------------------|--|
| ISO 9854-1:1994               | Thermoplastics pipes for the transport of fluids - Determination of pendulum impact strength by the Charpy method - Part 1: General test method                  |
| NEN-EN 10088-1:2005           | Stainless steels - Part 1: List of stainless steels  |
| NEN-EN-ISO 10147:2012         | Pipes and fittings made of crosslinked polyethylene (PE-X) - Estimation of the degree of crosslinking by determination of the gel content                        |
| NEN-EN 10283:2010             | Corrosion resistant steel castings   |
| NEN-ISO 10508: 2006           | Plastics piping systems for hot and cold water installations - Guidance for classification and design  |
| NEN-EN-ISO 11357-3: 2013      | Plastics - Differential scanning calorimetry (DSC) - Part 3: Determination of temperature and enthalpy of melting and crystallization                            |
| ISO 11922-1: 1997             | Thermoplastics pipes for the conveyance of fluids - Dimensions and tolerances - Part 1: Metric series  |
| NEN-EN 12293: 2000            | Plastics piping systems - Thermoplastics pipes and fittings for hot and cold water - Test method for the resistance of mounted assemblies to temperature cycling |
| NEN-EN 12294: 2000            | Plastics piping systems - Systems for hot and cold water - Test method for leaktightness under vacuum  |
| NEN-EN-ISO 15874-2: 2013      | Plastic piping systems for hot and cold water installations - Polypropylene (PP) –Part 2   |
| NEN-ISO 17455: 2005 / C1:2007 | Plastics piping systems - Multilayer pipes - Determination of the oxygen permeability of the barrier pipe  |

# I example IQC-scheme for product manufacturer



|  |                    |                    |                       |                                       |
|--|--------------------|--------------------|-----------------------|---------------------------------------|
| <b>A. Calibration of measuring and test equipment</b><br>Applicable procedure(s) nr(s):  |                    |                    |                       |                                       |
| Equipment to be calibrated   | Calibration aspect | Calibration method | Calibration frequency | Calibration file (name and location)  |
|  |                    |                    |                       |                                       |
|  |                    |                    |                       |                                       |
|  |                    |                    |                       |                                       |
| <b>B. Raw material and additives</b><br>Applicable procedure(s) nr(s):   |                    |                    |                       |                                       |
| <b>B.1 Receipt</b><br>For each delivery of raw material or additives data with respect to dates, producers, types and quantities are recorded as follows:  |                    |                    |                       |                                       |
| <b>B.2 Entry control</b>   |                    |                    |                       |                                       |
| Type of raw material   | Inspection aspect  | Inspection method  | Inspection frequency  | Registration file (name and location) |
|  |                    |                    |                       |                                       |
|  |                    |                    |                       |                                       |
| <b>C. Batch release tests per machine (including in-process and finished product testing)</b><br>Applicable procedure(s) nr(s):<br>Production process(es): |                    |                    |                       |                                       |
| Type of product  | Type of test       | Test method        | Test frequency        | Registration file (name and location) |
|  |                    |                    |                       |                                       |
|  |                    |                    |                       |                                       |
|  |                    |                    |                       |                                       |

Specific agreements/comments/explanations:



|  |              |             |                |  |
|--|--------------|-------------|----------------|--|
| <b>D. Process verification tests</b><br>Applicable procedure(s) nr(s): |              |             |                |  |
| Type of product  | Type of test | Test method | Test frequency | Registration file<br>(name and location) |
|  |              |             |                |  |
|  |              |             |                |  |

|   |  |  |  |  |
|---|--|--|--|--|
| <b>E. Control of nonconforming and/or rejected products</b><br>Applicable procedure(s) nr(s): |  |  |  |  |
| <b>E.1 Method of registration</b>   |  |  |  |  |
| <b>E.2 Method of identification</b>   |  |  |  |  |
| <b>E.3 Method of nonconformity review and disposition</b>                                     |  |  |  |  |

|   |                   |                      |  |  |
|---|-------------------|----------------------|--|--|
| <b>F. Inspection with regard to packaging, storage and transportation of the finished product</b><br>Applicable procedure(s) nr(s): |                   |                      |  |  |
| Inspection aspects  | Inspection method | Inspection frequency | Registration file<br>(name and location) |  |
| <b>F.1 Packaging/storage/ transportation etc</b>  |                   |                      |  |  |
|   |                   |                      |  |  |
|   |                   |                      |  |  |
|   |                   |                      |  |  |
|   |                   |                      |  |  |

Specific agreements/comments/explanations:

|   |   |                                  |
|---|---|----------------------------------|
| <b>Raw materials list</b><br>(not required to fill-out this appendix in case reference can be made to the CI ATA part of the certification agreement) |   | <b>Appendix I</b><br>Date: ..... |
| <b>I.1</b>  | <p>The product is built-up of the following raw materials:</p> <p>a) In case of products made from ready-made raw materials: listing of name and/or unique code of the raw material(s);</p> <p>b) In case of products made from own compounded raw materials: reference to raw material/compound sheets which are (only) available at the production location and which have to be authenticated by CI (e.g. by the CI inspector);</p> <p>c) In case of composed products (e.g. plastics fitting body, with separate nut, clamp ring and rubber sealing ring): of each part a specification according to a) or b) (whatever applicable).</p> <p>-</p> <p>-</p> <p>-</p> <p>-</p> <p>-</p> <p>-</p> <p>-</p> |                                  |

| <b>List of technical drawings</b> |              |                          | <b>Appendix II</b><br>Date:..... |
|-----------------------------------|--------------|--------------------------|----------------------------------|
| Drawing title and number          | Drawing date | Drawing title and number | Drawing date                     |
|                                   |              |                          |                                  |
|                                   |              |                          |                                  |
|                                   |              |                          |                                  |
|                                   |              |                          |                                  |
|                                   |              |                          |                                  |
|                                   |              |                          |                                  |
|                                   |              |                          |                                  |
|                                   |              |                          |                                  |

## **II example IQC-scheme for system holders**

|  |                           |   |
|--|---------------------------|---|
| <b>SCHEME<br/>INTERNAL QUALITY PLAN</b>  | Producer :                | Page nr. : 1  |
|  | Address :                 | Number of pages. :  |
|  | Address production site : | Annexes :   |
| <u>Scope(s)</u>  |                           |   |
| <u>Quality Control</u><br>Number of employee's in quality department :<br>Number of employee's in dayshift :<br>Number of employee's in nightshift : |                           | <u>Operating instructions and/ or quality manual</u><br>Operating instructions and procedures are registered as following: .....<br>.....<br>If no inspections are held during the night then the quality procedure: .....<br>Is followed |
| <u>Samplesystem</u><br>Applied system: .....   |                           | <u>Complaint procedure</u><br>The complaint procedure is recorded in .....<br>.....   |
| <u>Storage of the control data</u><br>All control data is to be kept for a minimum of.....year.  |                           | <u>Correcting measures</u><br>The procedure correcting measures is recorded in .....<br>.....   |
| <u>Agreements/ clarification</u>   |                           | Signature of the producer:<br><br><br><br><br><br><br><br><br><br>Date:   |



| <b>B. Inspection of the packaging, storage and transportation of the finished product</b><br>The guidelines for packing, storage and transport are listed in annex..... |                                 |                                    |   | Page nr. : 3                  |
|---|---------------------------------|------------------------------------|---|-------------------------------|
| <b>What is checked</b>  | <b>What aspects are checked</b> | <b>How will the checks be made</b> | <b>With what frequency are the checks performed</b> | <b>Method of registration</b> |
| B.1 Packaging   |                                 |                                    |   |                               |
|   |                                 |                                    |   |                               |
|   |                                 |                                    |   |                               |
|   |                                 |                                    |   |                               |
|   |                                 |                                    |   |                               |
|   |                                 |                                    |   |                               |
| B.2 Storage   |                                 |                                    |   |                               |
|   |                                 |                                    |   |                               |
|   |                                 |                                    |   |                               |
|   |                                 |                                    |   |                               |
|   |                                 |                                    |   |                               |
|   |                                 |                                    |   |                               |
| B.3 Transport   |                                 |                                    |   |                               |
|   |                                 |                                    |   |                               |
|   |                                 |                                    |   |                               |
|   |                                 |                                    |   |                               |



|   |                     |
|---|---------------------|
| <b>E. Complaints procedure</b><br>The complaints procedure is detailed in the Qualitymanual procedure ..... | <b>Page nr. : 5</b> |
| <b>E.1 Receiving the complaint</b><br>.....<br>.....<br>.....<br>.....<br>.....                             |                     |
| <b>E.2 Research of the cause</b><br>.....<br>.....<br>.....<br>.....<br>.....                               |                     |
| <b>E.3 Handeling of the complaint</b><br>.....<br>.....<br>.....<br>.....<br>.....<br>.....                 |                     |

**Special agreements/ clarification:**